

Technical Data Sheet

ACTDigi® DUV-9454

UV curable gloss screen applied digital high adhesion coating


Product Description

High gloss, screen or blanket applied topcoat with exceptional flow and wetting. Specifically developed for Konica Minolta or other DEP-type inks.

General Information	
Product Type	Coatings
Product Technology	UV curing
Field Of Application	Publication & Commercial, Books, Brochures, Catalogs, Commercial, Direct Mail
Optic	Glossy

Properties

- Gloss
- Reactivity
- Scuff Resistance
- Slip Surface Smoothness
- Flexibility
- Two Sided Coating



Product Characteristics			
Viscosity	• ~280 mPas +/- 15 (Centipoise at 25°C)		
Curing	• 75-100 fpm @ 300WPI		
Hot Foil Stamping	No	Glueability	No
Slip Angle	14 +/- 3 degrees	Anti Penetration	No

Substrate Recommendation

- Coated Board
- Coated Paper

Application Method

- 355 - 460 mesh screen

Technical Data Sheet

ACTDigi® DUV-9454

UV curable gloss screen applied digital high adhesion coating

Storage Instructions

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.

Cleaning Instructions

- Please clean machines and tools with commercial cleaning agents.

Additional Information

MEK Resistance: 25 - 35 Double Rubs

* Estimated chemical resistance on press

Contact Information

ACTEGA North America, Inc.

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA@altana.com

www.actega.com

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.