

Technical Data Sheet
ACTGreen® BARRIER CTG AQ2149200
Aqueous Matte Barrier Top Coat


Product Description

Aqueous matte barrier top coat for food packaging on inside or outside of the package

General Information	
Product Type	Coatings
Product Technology	Water based
Field Of Application	Paperbased Packaging, Barrier: FastFood, Barrier: Laundry/HomeCare, Barrier: Confect, Folded Boxes-Dry Food/Dry Beverages/Baby Food, Folded Boxes-Frozen Food/Dairy products
Properties	Good printability, good adhesion, Good water resistance, good Cobb values, Proves in practice to be suitable as coating for the later counter glueing., Temporary barrier against oil, fat and water
Optic	Matte

Properties

Gloss
Scuff Resistance
Counter Glueing



Product Characteristics			
Viscosity	• ~ s -2 (19-22) (#3 Zahn Cup at 23°C)		
Hot Foil Stamping	No	Glueability	No
Drying AQ	• Hot air knives with air evacuation	Anti Penetration	No
Barrier Properties	• Temporary barrier against fat • Temporary barrier against oil • Temporary barrier against water		

Substrate Recommendation

- Coated Board
- Uncoated board

Technical Data Sheet

ACTGreen® BARRIER CTG AQ2149200

Aqueous Matte Barrier Top Coat

Application Method

- Performance characteristics will vary depending upon coating film weight and substrate porosity. A “pinhole” free coating is critical for best results. It is imperative that the coating, ink, and substrate combination is pre-qualified prior to commercial production. For very porous paper, a primer such as ACTGreen® Barrier Coating AQ-17S is recommended.

Printing Equipment and Anilox Recommendation	
Printing Equipment	Anilox Volume
Rod Coater or Large Volume Anilox Coater #6 - #10 Rod Anilox: 120 – 180 LPI / greater than 20 BCM	- cm ³ /m ² / -

Storage Instructions

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.
- Protect from frost, heat and sun exposure. Storage may cause a change in viscosity. We recommend to check the viscosity and adjust - if necessary - with water.

Cleaning Instructions

- Please clean machine and tools immediately with room temperature water or hot water. In cases where the coating has been left to dry, warm water and INKO Cleaner may be required.

Regulatory Compliance

- Disclaimer: For regulatory compliances please reach out to your responsible ACTEGA contact person.

Additional Information

3M #7 Kit: Pass

3M #12 Kit: Pass

Cobb Values: 2.12 grams/cm²

Cobb Values (w/Primer): 1.40 grams/cm²

MVTR Values: 1,083 grams/m²/day

MVTR Values (w/Primer): 417 grams/m²/day

All values above were tested with a coating weight of 1Mil Wet, unless otherwise noted. Primer and Top Coat combinations were tested at 2.0 Mils total (Primer at 1 Mil and Top Coat at 1 Mil). Testing was performed under laboratory conditions, with coating applied on the uncoated side of 14 pt. Everest C1S. These values represent typical laboratory testing results and should not be interpreted as specifications.

Technical Data Sheet

ACTGreen® BARRIER CTG AQ2149200

Aqueous Matte Barrier Top Coat

Contact Information

ACTEGA North America, Inc.

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA@altana.com

www.actega.com

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.