

**Technical Data Sheet**  
**STARKOTE® AQ-222**

Aqueous gloss heat resistant coating

ACTEGA North America, Inc.  
1450 Taylors Lane, Cinnaminson, NJ 08077 US  
+1 800-255-0021  
info.ACTEGA.northamerica@altana.com  
www.actega.com

**Product Description**

Aqueous gloss heat resistant coating with hot-tack resistance

General Information	
Product Type	Coatings
Product Technology	Water based
Field Of Application	Paperbased Packaging, Decorative packaging, exterior, Heat-treated paper applications, Shelf-ready packaging
Properties	Good printability, good adhesion, High heat resistance, Has proven itself as a coating for the rearside of board., Suitable for the two-sided coating

**Application Method**


- Blanket, Tower, Dampener and Anilox Coaters, 9-11 bcm

**Substrate Recommendation**

- Coated Board
- Coated Paper
- Pre-print liner

**Properties**

- Gloss
- Scuff Resistance
- Slip Surface Smoothness
- Two Sided Coating



Product Characteristics			
Viscosity	• ~ s -1 (15-18) -2 (19-22) -3 (23-26) (#3 Zahn Cup at 23°C)		
Hot Foil Stamping	<input type="checkbox"/>	Glueability	<input type="checkbox"/>
Drying AQ	• Hot air knives with air evacuation	Slip Angle	16 +/- 2 degrees

**Technical Data Sheet**

**STARKOTE® AQ-222**

Aqueous gloss heat resistant coating

**ACTEGA North America, Inc.**

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA.northamerica@altana.com

www.actega.com

Product Characteristics			
Heat Resistance	Heat Release: 400°F @ 3 seconds dwell @ 80 PSI Block Resistance: 275°F @ 16 hrs @ 2 PSI	Anti Penetration	<input type="checkbox"/>

**Storage Instructions**

- Shelf-life 12 months
- Applies to closed original containers at 5°C up to 30°C.
- Protect from frost, heat and sun exposure. Storage may cause a change in viscosity. We recommend to check the viscosity and adjust - if necessary - with water.

**Cleaning Instructions**

- Please clean machine and tools immediately with room temperature water or hot water. In cases where the coating has been left to dry, warm water and INKO Cleaner may be required.

**Disclaimer**

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.