

Technical Data Sheet

MOTIONCOAT® 4251

UV curable gloss topcoating for use with MotionCoat® varnish


Product Description

MotionCoat® 4251 is applied overall, through the anilox/blanket coater, over the pattern applied with Motioncoat® 42 Litho Primer.

General Information	
Product Type	Coatings
Product Technology	UV curing
Field Of Application	Paperbased Packaging, Publication & Commercial, Advertising, Brochures, Catalogs, Commercial, Cosmetic packaging, Decorative packaging, exterior, Displays, Folded Boxes-Household/Hardware & Electronics/other non food, Folded Boxes-Personal Care/Cosmetics, Other Specialities, Photo books, Shelf-ready packaging, Transport packaging
Properties	Enables an even and structured surface, Good printability, good adhesion, Print varnish to get glossy-, matte and/or trickle down effects by the inline coating with UV varnishes. The print varnish must be UV cured before overprinting., Proves in practice to be suitable as two-sided coating.
Optic	Glossy

Properties

- Gloss
- Reactivity
- Scuff Resistance
- Slip Surface Smoothness
- Flexibility
- Two Sided Coating
- Counter Glueing



Product Characteristics			
Viscosity	• ~850 mPas +/- 50 (Centipoise at 25°C)		
Curing	• 125 fpm @ 300WPI		
Hot Foil Stamping	No	Glueability	No
Anti Penetration	No		

## Technical Data Sheet

### MOTIONCOAT® 4251

UV curable gloss topcoating for use with MotionCoat® varnish

#### Substrate Recommendation

- Coated Board
- Coated Paper
- Metallized Substrate

#### Application Method

- Blanket, Flexo or Chambered Anilox Coaters, 10-14 bcm; Please refer to ACTEGA's usage guide for the set up and application techniques to create the best Motioncoat effects in combination with the Motioncoat first down varnish.

#### Storage Instructions

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.

#### Cleaning Instructions

- Please clean machines and tools with commercial cleaning agents.

#### Additional Information

MEK Resistance: 20 - 40 Double Rubs

\* Estimated chemical resistance on press

#### Contact Information

ACTEGA North America, Inc.

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA@altana.com

www.actega.com

#### Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.