

Technical Data Sheet

STARKOTE® AQ-149

Aqueous gloss non-skid coating


Product Description

Aqueous gloss non-skid coating with a 28 degree slide angle

General Information	
Product Type	Coatings
Product Technology	Water based
Field Of Application	Paperbased Packaging, Folded Boxes-Beverage Carriers, Folded Boxes-Household/Hardware & Electronics/other non food, Folded Boxes:Spirits/Wine, Frozen food packaging
Properties	Good printability, good adhesion, Good rub and scratch resistance, High friction values, Proves in practice to be suitable as coating for the later counter glueing.
Optic	Glossy

Properties

- Gloss
- Scuff Resistance
- Slip Surface Smoothness
- Hot Foil Stamping
- Two Sided Coating
- UV Varnishing
- Counter Glueing



Product Characteristics			
Viscosity	• ~ s -1 (15-18) -2 (19-22) (#3 Zahn Cup at 23°C)		
Hot Foil Stamping	No	Glueability	No
Drying AQ	• Hot air knives with air evacuation	Slip Angle	28 +/- 2 degrees
Heat Resistance	140°F @ 16 hrs @ 2 PSI	Anti Penetration	No

Substrate Recommendation

- Coated Board

Application Method

- Blanket, Tower, Dampener and Anilox Coaters, 9-11 bcm

Technical Data Sheet

STARKOTE® AQ-149

Aqueous gloss non-skid coating

Storage Instructions

- Shelf-life 12 months
- Applies to closed original containers at 5°C up to 30°C.
- Protect from frost, heat and sun exposure. Storage may cause a change in viscosity. We recommend to check the viscosity and adjust - if necessary - with water.

Cleaning Instructions

- Please clean machine and tools immediately with room temperature water or hot water. In cases where the coating has been left to dry, warm water and INKO Cleaner may be required.

Contact Information

ACTEGA North America, Inc.

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA@altana.com

www.actega.com

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.