

Technical Data Sheet
STARKOTE® AQ-20
Aqueous satin primer


Product Description

Aqueous satin primer, foil stampable and glueable

General Information	
Product Type	Coatings
Product Technology	Water based
Field Of Application	Publication & Commercial, Books, Brochures, Commercial, Cosmetic packaging, Decorative packaging, exterior, Displays, Other non-food, Shelf-ready packaging
Properties	An overcoating with UV varnishes and water based coatings is possible., Good wetting on different printing inks, e. g. conventional, UV printing inks, web offset printing inks, make tests!, Suitable for the two-sided coating, Very suitable for hot foil stamping, Suitability of foils must be checked
Optic	Semi gloss

Properties

- Gloss
- Scuff Resistance
- Slip Surface Smoothness
- Hot Foil Stamping
- Two Sided Coating
- UV Varnishing
- Counter Glueing



Product Characteristics			
Viscosity	• ~ s -1 (15-18) -2 (19-22) -3 (23-26) (#3 Zahn Cup at 23°C)		
Hot Foil Stamping	No	Glueability	No
Drying AQ	• Hot air knives with air evacuation	Slip Angle	24 +/- 2 degrees
Heat Resistance	130°F @ 16 hrs @ 2 PSI	Anti Penetration	No

Substrate Recommendation

- Coated Board
- Coated Paper

Technical Data Sheet

STARKOTE® AQ-20

Aqueous satin primer

Application Method

- Blanket, Tower, Dampener and Anilox Coaters, 9-11 bcm

Storage Instructions

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.
- Protect from frost, heat and sun exposure. Storage may cause a change in viscosity. We recommend to check the viscosity and adjust - if necessary - with water.

Cleaning Instructions

- Please clean machine and tools immediately with room temperature water or hot water. In cases where the coating has been left to dry, warm water and INKO Cleaner may be required.

Contact Information

ACTEGA North America, Inc.

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA@altana.com

www.actega.com

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.