

Technical Data Sheet
TERRAWET Gloss Coating G 9/640-040 FoodSafe
for the direct contact with dry/fat-including food, Material Health Certificate (Gold)

Product Description

Water-based gloss coating with excellent drying and a very high wet block resistance. The product is suitable for the two-sided coating and counter glueing. It also offers a temporary barrier against fat and water.


The coating belongs to our FoodSafe series.
FoodSafe is our portfolio of water-based coatings that are suitable for a direct contact to dry and fat-including foodstuffs according to the Framework Regulation EU No. 1935/2004.
These coatings have a low potential for migration and they do not contain undesirable constitutional components such as mineral oils (MOSH, MOAH), heavy metals or phthalates.

This product has been assessed against the criteria of the Material Health category in the Cradle to Cradle Certified™ Product Standard and was awarded a Gold level Material Health Certificate by the Cradle to Cradle Products Innovation Institute.

General Information	
Product Type	Coatings
Product Technology	Water based
Field Of Application	Paperbased Packaging, Publication & Commercial, Displays, Sweets, Food direct, Other non-food, Food indirect, Beverages, Personal Care, Pharma, Frozen food packaging, Dry foodstuff packagings, Detergent packaging, CSD, Brochures
Properties	Temporary barrier against fat and water, Listed in the Sony Green Book (Sony Green Partner)
Optic	Glossy

Properties

- Gloss
- Drying
- Scuff Resistance
- Hot Foil Stamping
- Crackling Tolerance
- Foaming Tolerance
- Two Sided Coating
- Wet Block Resistance
- UV Varnishing
- Counter Glueing
- Foil Laminator



Product Characteristics			
Viscosity	<ul style="list-style-type: none">~60 s (20°C, DIN 4 mm cup)~40 s (20°C, DIN 4 mm cup)		
Hot Foil Stamping	Yes	Glueability	No

Technical Data Sheet

TERRAWET Gloss Coating G 9/640-040 FoodSafe

for the direct contact with dry/fat-including food, Material Health Certificate (Gold)

Product Characteristics			
Slip Angle	15° - 19°	Heat Resistance	Up to 180°C
Anti Penetration	No		

Substrate Recommendation

- Metallized substrates
- Aluminum foil laminated substrates
- Coated Board
- Rearside PE coated board
- Coated Paper

Application Method

- Wet-in-wet
- Gravure Printing
- Sheet-fed offset, coating unit (chambered doctor blade or roller system)
- Sheet-fed offset, coating unit
- Resistance against alkali, alcohol and solvents should be given according to DIN ISO 2836, formerly DIN 16524, in order to exclude a change of colour.
- Please use printing inks/foil inks suitable for coating.
- We recommend to omit adhesive straps.
- There must be a suitability for water-based coating if anti-set-off powder is used (do not use mineral powder).
- Stir well before use! Mechanical stirring is recommended.
- For the further processing of the sheets under mechanical load and/or the influence of humidity, a sufficient high basic consistency of the substrate is required.
- The coating is suitable for wrapping in foils XS and MS (no acrylic coated foil).
- Recommended coating application: 3,5 - 5 g/m²; wet
- The full profile of characteristics of the coating film is available after complete drying.
- Recommended pile temperature: not > 35°C.
- Using non-absorbent substrates and / or slowly absorbent printing inks, we recommend to plan for the corresponding drying times.
- In order to guarantee a fast and complete drying, we recommend a sufficient airing of the sheets.
- Viscosity for processing in gravure printing: 15-20 sec. (dilution with water:ethanol 3:1).
- There must be a sufficient hardening of the overall system substrate-printing ink-coating before further processing which should be checked in the process.

Storage Instructions

- Storage (Days): 365
- Shelf-life 18 months
- Storage may cause a change in viscosity. We recommend to check the viscosity and adjust - if necessary - with water.
- Applies to closed original containers at 5°C up to 30°C.
- Avoid mixing with other coatings or washing water.
- Protect from frost, heat and sun exposure.

Cleaning Instructions

- Please clean machines and tools immediately with water. Dried coating residues can be removed with TERRAWET Clean Cleaning Agent G 12/181.

Technical Data Sheet

TERRAWET Gloss Coating G 9/640-040 FoodSafe

for the direct contact with dry/fat-including food, Material Health Certificate (Gold)

Regulatory Compliance

- For information about the food legislation assessment of this product (e. g. demands on the Nestlé Standard St-80.001 „Printing Inks for Food Packaging" (version 04-2022) and the Swiss Ordinance (SR 817.023.21 - ordinance of the Swiss Confederation on materials & articles in contact with food) or FDA & California Proposition 65) we ask you to contact our department for quality, environment and product safety.
- P: +49 (0) 5132 5009-140;
- ehsqrlhrte.actega@altana.com

Contact Information

ACTEGA GmbH, Plant Lehrte

Industriestraße 12, 31275 Lehrte DE

+49 5132 5009-0

info.ACTEGA@altana.com

www.actega.com

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.