

Technical Data Sheet
ULTRASHEEN® UV-9200
UV curable high gloss coating


Product Description

UV curable high gloss coating with excellent flexibility

General Information	
Product Type	Coatings
Product Technology	UV curing
Field Of Application	Paperbased Packaging, Publication & Commercial, Advertising, Books, Brochures, Catalogs, Commercial, Decorative packaging, exterior, Displays, Folded Boxes-Household/Hardware & Electronics/other non food, Folded Boxes-Personal Care/Cosmetics, Folded Boxes:Spirits/Wine, Magazines, Other non-food, Photo books, Shelf-ready packaging
Properties	Good flow out, Good printability, good adhesion, High flexibility (fold/crease), The coating contains optical brightener.
Optic	Glossy

Properties

- Gloss
- Reactivity
- Scuff Resistance
- Slip Surface Smoothness
- Flexibility
- Two Sided Coating



Product Characteristics			
Viscosity	• ~250 mPas +/- 20 (Centipoise at 25°C)		
Curing	• 125 fpm @ 300WPI		
Hot Foil Stamping	No	Glueability	No
Slip Angle	13 +/- 3 degrees	Anti Penetration	No

Substrate Recommendation

- Coated Board
- Coated Paper

Technical Data Sheet

ULTRASHEEN® UV-9200

UV curable high gloss coating

Application Method

- Blanket, Flexo or Chambered Anilox Coaters, 10 - 14 bcm

Storage Instructions

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.

Cleaning Instructions

- Please clean machines and tools with commercial cleaning agents.

Additional Information

MEK Resistance: 20 - 30 Double Rubs

* Estimated chemical resistance on press

Contact Information

ACTEGA North America, Inc.

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA@altana.com

www.actega.com

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.