

# Technical Data Sheet ULTRASHEEN® UV-9733

UV curable smooth matte coating


# **Product Description**

UV curable smooth matte coating

| General Information  |  |  |  |
|----------------------|--|--|--|
| Product Type         | Coatings   |  |  |
| Product Technology   | UV curing  |  |  |
| Field Of Application | Publication & Commercial, Advertising, Books, Brochures,<br>Catalogs, Commercial, Decorative packaging, exterior,<br>Displays, Magazines                                       |  |  |
| Properties           | Good flow out, Good rub and scratch resistance, Low tendency to penetration, Proves in practice to be suitable as two-sided coating., The coating contains optical brightener. |  |  |
| Optic                | Matte  |  |  |

# **Properties**

Gloss
Reactivity
Scuff Resistance
Slip Surface Smoothness
Flexibility
Two Sided Coating



| Product Characteristics |   |             |    |
|-------------------------|---|-------------|----|
| Viscosity               | • ~290 mPas +/- 20 (Centipoise at 25°C) |             |    |
| Curing                  | • 125 - 150 fpm @ 300WPI                |             |    |
| Hot Foil Stamping       | No                                      | Glueability | No |
| Anti Penetration        | No                                      |             |    |

# **Substrate Recommendation**

- Coated Board
- Coated Paper

# **Application Method**

• Blanket, Flexo or Chambered Anilox Coaters, 10-14 bcm



# Technical Data Sheet ULTRASHEEN® UV-9733

UV curable smooth matte coating

### **Storage Instructions**

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.

### Cleaning Instructions

• Please clean maschines and tools with commercial cleaning agents.

#### Additional Information

MEK Resistance: 15 - 25 Double Rubs
\* Estimated chemical resistance on press

#### **Contact Information**

ACTEGA North America, Inc. 1450 Taylors Lane, Cinnaminson, NJ 08077 US +1 800-255-0021 info.ACTEGA@altana.com www.actega.com

#### Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.