

Technical Data Sheet
ULTRASHEEN® UV-9751
UV curable matte web offset coating


Product Description

UV curable matte web offset coating with high adhesion

General Information	
Product Type	Coatings
Product Technology	UV curing
Field Of Application	Publication & Commercial, Catalogs, Magazines
Properties	Good flow out, High flexibility (fold/crease), Proves in practice to be suitable as two-sided coating., The coating contains optical brightener.
Optic	Matte

Properties

- Gloss
- Reactivity
- Scuff Resistance
- Slip Surface Smoothness
- Flexibility
- Two Sided Coating



Product Characteristics			
Viscosity	• ~375 mPas +/- 25 (Centipoise at 25°C)		
Curing	• 150 fpm @ 300WPI		
Hot Foil Stamping	No	Glueability	No
Anti Penetration	No		

Substrate Recommendation

- Coated Paper

Application Method

- Blanket, Flexo or Chambered Anilox Coaters, 10-14 bcm

Technical Data Sheet

ULTRASHEEN® UV-9751

UV curable matte web offset coating

Storage Instructions

- Shelf-life 4 months
- Applies to closed original containers at 5°C up to 30°C.

Cleaning Instructions

- Please clean machines and tools with commercial cleaning agents.

Additional Information

MEK Resistance: 15 - 25 Double Rubs

* Estimated chemical resistance on press

Contact Information

ACTEGA North America, Inc.

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA@altana.com

www.actega.com

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.