

Technical Data Sheet

ULTRASHEEN® UV9413A

UV curable gloss screen coating


Product Description

UV curable gloss screen coating with high adhesion and flexibility

General Information	
Product Type	Coatings
Product Technology	UV curing
Field Of Application	Paperbased Packaging, Advertising, Brochures, Catalogs, Commercial, Decorative packaging, exterior, Other non-food, Books
Properties	Balanced development of gloss on different board surfaces., Good wetting on different printing inks, e. g. conventional, UV printing inks, web offset printing inks, make tests!, Suitable for the two-sided coating, The coating contains optical brightener.
Optic	High gloss

Properties

- Gloss
- Reactivity
- Scuff Resistance
- Slip Surface Smoothness
- Flexibility
- Two Sided Coating



Product Characteristics			
Viscosity	• ~380 mPas +/- 20 (Centipoise at 25°C)		
Curing	• 75 - 100 fpm @ 300WPI		
Hot Foil Stamping	No	Glueability	No
Slip Angle	16 +/- 2 degrees	Anti Penetration	No

Substrate Recommendation

- Coated Board
- Coated Paper

Application Method

- Flatbed and Rotary Screen, 355-420 mesh screen

Technical Data Sheet

ULTRASHEEN® UV9413A

UV curable gloss screen coating

Storage Instructions

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.

Cleaning Instructions

- Please clean machines and tools with commercial cleaning agents.

Additional Information

MEK Resistance: 30 - 40 Double Rubs

* Estimated chemical resistance on press

Contact Information

ACTEGA North America, Inc.

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA@altana.com

www.actega.com

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.