

Technical Data Sheet

**ULTRASHEEN® UVG1992BF**

UV curable gloss benzophenone-free coating


Product Description

UV curable gloss benzophenone-free coating with excellent flexibility, adhesion and fast cure

General Information	
Product Type	Coatings
Product Technology	UV curing
Field Of Application	Paperbased Packaging, Publication & Commercial, Books, Brochures, Corrugated, Decorative packaging, exterior, Displays, Envelopes, Folded Boxes-Household/Hardware & Electronics/other non food, Folded Boxes-Personal Care/Cosmetics, Folded Boxes:Spirits/Wine, Magazines, Personal Care, Photo books, Shelf-ready packaging, Transport packaging
Properties	Benzophenone-Free, Chemical resistance, For absorbent and non absorbent surfaces, Good printability, good adhesion, Good wetting on different printing inks, e. g. conventional, UV printing inks, web offset printing inks, make tests!, High flexibility (fold/crease), Proves in practice to be suitable as two-sided coating., The coating contains optical brightener., Very good flow out
Optic	High gloss

Properties

- Gloss
- Reactivity
- Scuff Resistance
- Slip Surface Smoothness
- Flexibility
- Two Sided Coating



Product Characteristics			
Viscosity	• ~270 mPas +/- 30 (Centipoise at 25°C)		
Curing	• 125 - 150 fpm @ 300WPI		
Hot Foil Stamping	No	Glueability	No
Slip Angle	14 +/- 2 degrees	Anti Penetration	No

## Technical Data Sheet

### ULTRASHEEN® UVG1992BF

UV curable gloss benzophenone-free coating

## Substrate Recommendation

- Coated Board
- Coated Paper

## Application Method

- Blanket, Flexo or Chambered Anilox Coaters, 10-14 bcm

## Storage Instructions

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.

## Cleaning Instructions

- Please clean machines and tools with commercial cleaning agents.

## Additional Information

MEK Resistance: 20 - 30 Double Rubs

\* Estimated chemical resistance on press

## Contact Information

**ACTEGA North America, Inc.**

1450 Taylors Lane, Cinnaminson, NJ 08077 US

+1 800-255-0021

info.ACTEGA@altana.com

www.actega.com

## Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.