

Technical Data Sheet (Preliminary)



TPE PROVAMED® D1341 TP

Application

Injection Molding of Elastic Parts, Extrusion

02.05.2019

	Unit	Method ¹	
Physical Properties			
Specific Gravity	[g/cm ³]	ISO 1183	0,99
Melt Flow Rate			
190 °C, 5 kg	[g/10min]	ISO 1133	22
200 °C, 5 kg	[g/10min]	ISO 1133	34
melt density	[g/cm ³]	ISO 1133	0,9
Mechanical Properties			
Hardness			
Shore A	[-]	ASTM D 2240, 5 s	90
Shore D	[-]	ASTM D 2240, 5 s	43
Tensile Strength	[MPa]	DIN 527-2	13,1
Elongation at Break	[%]	DIN 527-2	290
Tensile Modulus	[MPa]	DIN 527-2	800
Thermal Properties			
Differential Scanning Calorimetry ²			
Glass Transition Temperature ³	[°C]	ADS - Method	-
Optical Properties			
Transparency			transparent
Sterilization			
Steam Sterilization ⁴ 121/134 °C			no/no
Ethylene Oxide ⁵			yes
Gamma Radiation ⁶			yes
Regulatory			
USP VI			yes
ISO10993			yes
Processing Properties for Injection Molding			
Processing Temperatures			
Hopper	[°C]		20-30
Barrel	[°C]		140-200
Nozzle	[°C]		170-240
Mould	[°C]		20-40

Storage Conditions

Protected from direct sunlight, temperatures exceeding 40°C, humidity and sources of off-odors.

A member of ALTANA

(1) According to (2) Heating rate 10 K/min (3) Second heating cycle (4) 15 min. (5) 1 and 3 cycles, 270-500 mg/l (6) 25 and 50 kGy

(7) See separate bulletin on sterilization

TDS_TPE_PROVAMED® D1341 TP_Version_0_072018

Recommendations, suggestions or statements made in this bulletin are to the best of our knowledge and must not be regarded legal warranty or as involving any liability on side of Actega DS. These data must be understood in conjunction with our General Conditions of Sale which apply to all goods supplied by us. We retain the right to make changes in the specification due to improvements or changes in production methods. Use in long-term implantations and/or class III medical products is not intended and Actega DS takes no legal warranty for such use.