

Technical Datasheet

23.09.2021

TERRAWET Matt Coating G 9/131 silk matt-040


1 / 2

Product description

Water-based semi-matt coating with fast drying and a very high wet block resistance.

- Sheet-fed offset, coating unit (chambered doctor blade or roller system)

Properties

	
Gloss	■ ■ ■ ■ □ □ □ □ □ □
Scuff resistance	■ ■ ■ ■ ■ ■ ■ ■ □ □ □ □
Hot foil stamping	■ ■ ■ ■ ■ ■ ■ ■ □ □ □ □
Crackling tolerance	■ ■ ■ ■ ■ ■ ■ ■ □ □ □ □
Foaming tolerance	■ ■ ■ ■ ■ ■ ■ ■ □ □ □ □
Drying	■ ■ ■ ■ ■ ■ ■ ■ □ □ □ □
Two-sided coating	■ ■ ■ ■ ■ ■ ■ ■ □ □ □ □
Wet block resistance	■ ■ ■ ■ ■ ■ ■ ■ ■ ■ ■ ■
UV varnishing	■ ■ ■ ■ ■ ■ ■ ■ □ □ □ □
Counter glueing	■ ■ ■ ■ ■ ■ ■ ■ □ □ □ □
Slip angle	20° -24°
Foil lamination	■ ■ ■ ■ ■ ■ □ □ □ □ □ □
Heat resistance	up to 120°C

Substrate

- Coated paper
- Coated board
- Rearside PE coated board

Legislation assessment

- In principal the product can be used as directed and with a complete drying for the coating of foodstuff packagings for the indirect contact to the filling good. For information about the food legislation assessment of this product (e. g. demands on the Nestlé "Guidance Note on Packaging Inks" and the Swiss Ordinance (SR 817.023.21 - ordinance of the Swiss Confederation on materials & articles in contact with food)) we ask you to contact our department for quality, environment and product safety. T: +49 (0) 5132 5009-140 mail to: QUM.ACTEGA.Terra @altana.com

Material characteristics

- Viscosity: 40 sec. (20°C, DIN 4 mm cup)

Application (End Uses)

- Wet glue (Other non-food, Beverages)
- Commercials (Brochures)
- Folded boxes (Other non-food, Food indirect, Dry foodstuff packagings)
- Corrugated (Displays)

Processing recommendations

- Resistance against alkali, alcohol and solvents should be given according to DIN ISO 2836, formerly DIN 16524, in order to exclude a change of colour.
- The full profile of characteristics of the coating film is available after complete drying.
- There must be a sufficient hardening of the overall system substrate-printing ink-coating

Processes

- Wet-in-wet

Technical Datasheet

23.09.2021

TERRAWET Matt Coating G 9/131 silk matt-040

2 / 2

- before further processing which should be checked in the process.
- For the further processing of the sheets under mechanical load and/or the influence of humidity, a sufficient high basic consistency of the substrate is required.
 - There must be a suitability for water-based coating if anti-set-off powder is used (do not use mineral powder).
 - The coating is suitable for wrapping in foils XS and MS (no acrylic coated foil).
 - In order to guarantee a fast and complete drying, we recommend a sufficient airing of the sheets.
 - Please use printing inks/foil inks suitable for coating.
 - Recommended coating application: 3,5 - 5 g/m²/wet
 - Stir well before use!
Mechanical stirring is recommended.
 - Recommended pile temperature: not > 35°C
 - We recommend to omit adhesive straps.
 - Using non-absorbent substrates and / or slowly absorbent printing inks, we recommend to plan for the corresponding drying times.

Cleaning instructions

- Please clean machines and tools immediately with water. Dried coating residues can be removed with TERRAWET Clean Cleaning Agent G 12/180.

Storage instructions

- Shelf-life 18 months
- Storage may cause a change in viscosity. We recommend to check the viscosity and adjust - if

- necessary - with water.
- Applies to closed original containers at 5°C up to 30°C.
 - Protect from frost, heat and sun exposure.
 - Avoid mixing with other coatings or washing water.

Disclaimer

- This data sheet does not claim to be complete.
- All information are technical quality descriptions, advisory and due to the wide range of materials, production conditions, operations and processes they do not release from own tests and examinations under customer-specific circumstances.
- If an application is intended to be made under different conditions than those specified in this sheet, we only assume liability after having examined the respective different conditions.
- We reserve the right to change product characteristics due to technical progress, amendment of applicable law and mandatory production-related needs.
- All information provided on this product (in this sheet or elsewhere) are made to the best of our knowledge.